## SUPER SMOOTH

#### **DIDYOU KNOW**

Accent Opaque Super Smooth is often used as an alternative to coated paper?

Coating helps to keep the ink on the surface of the paper, which creates crisp text and images, but the same effect can be achieved through calendering, or passing the paper through steel rolls that exert pressure and compress the fibers. This process ensures the surface of the paper is extremely level and uniform.

The smoother the paper, the better the ink holdout, and Accent Opaque Super Smooth is highly calendered. This, combined with its 97 brightness, is why Accent makes colors pop! Plus, the soft, satiny texture makes it ideal for high-end collateral or brand promotions.



# SUPER SMOOTH

TEXT / COVER

#### **VALUE**

Leave room in the budget for finishing with a premium product at a not-so-premium price.

#### **PERFORMANCE**

High brightness and super smooth texture together ensure a bright, consistent on-press performance whether you print offset, digital inkjet or Indigo<sup>®</sup>.

#### VARIETY

Choose from sheets in 5 basis weights, rolls in 4 basis weights, white and warm white colors and options with ImageLok® Technology for optimization on digital inkjet devices or Indigo treatment for optimization on HP® Indigo devices.

#### **AVAILABILITY**

Accent Opaque Super Smooth is there when you need it. Talk to your International Paper sales representative to learn more about delivery times specific to you.

### **SUSTAINABILITY**

Communicate a warm, natural message with the Forest Stewardship Council® (FSC) certified Accent Opaque Super Smooth.

TEXT / WHITE / SUPER SMOOTH						OVERVIEW		
BASIS WT.	GSM	CALIPER	SMOOTHNESS	BRIGHTNESS	OPACITY	CERTIFICATION	PC FIBER	
70	104	4.7	60	97	94	FSC	0%	
80	118	5.5	60	97	96	FSC	0%	
100	148	6.7	60	97	97	FSC	0%	

COVER / WHITE / SUPER SMOOTH						OVERVIEW		
BASIS WT.	GSM	CALIPER	SM00THNESS	BRIGHTNESS	OPACITY	CERTIFICATION	PC FIBER	
65	176	8.0	80 *[60]	97	98.0	FSC	0%	
80	216	10.0	80 *[60]	97	99.0	FSC	0%	
100	271	12.0	60	97	99.0	FSC	0%	
	*[60] indicates 60 smoothness on specific skus.							

COVER / WARM WHITE / SUPER SMOOTH						OVERVIEW		
BASIS WT.	GSM	CALIPER	SMOOTHNESS	BRIGHTNESS	OPACITY	CERTIFICATION	PC FIBER	
65	176	8.0	60	-	98.0	FSC	0%	
80	216	10.0	60	-	99.0	FSC	0%	
100	271	12.0	60	_	99.0	FSC	0%	

ACCENTO /	<sup>®</sup> OPAQ ′ SUPE	OVERVIEW					
BASIS WT.	GSM	CALIPER	SM00THNESS	BRIGHTNESS	OPACITY	CERTIFICATION	PPI
60	89	4.2	70	97	93	ROLLS SFI	476
70	104	4.8	70	97	94	FSC / ROLLS SFI	417
80	118	5.6	70	97	96	FSC / ROLLS SFI	357
7pt/110*	163	7.4	70	97	98	ROLLS SFI	270
9pt/144	213	9.4	70	97	99	ROLLS SFI	213

\*Available as a make request.

INDIGO TREATED / TEXT / WHITE / SUPER SMOOTH OVER							'IEW
BASIS WT.	GSM	CALIPER	SMOOTHNESS	BRIGHTNESS	OPACITY	CERTIFICATION	PC FIBER
20/50	74	3.4	60	97	92	FSC	0%
24/60	89	4.0	60	97	93	FSC	0%
28/70	104	4.8	60	97	94	FSC	0%
32/80	118	5.6	60	97	96	FSC	0%
40/100	148	6.8	60	97	97	FSC	0%





©2021 Sylvamo Corporation. All rights reserved. Printed in USA.
Accent is a registered trademark of Sylvamo Corporation. HP and Indigo
are registered trademarks of HP Inc. Forest Stewardship Council and FSC
are registered trademarks of Forest Stewardship Council.